

FICHA TÉCNICA

DATA SHEET - FICHE TECHNIQUE

7 Años de garantía	36 Altura del hilo (mm)	DIAMANTE Forma del hilo	4 Colores	21.420 Puntadas m ²	1.892 Peso hilo gr/m ²	2.863 Peso con backing gr/m ²
------------------------------	-----------------------------------	-----------------------------------	---------------------	--	---	--

Aplicaciones - Applications - Anwendung - Applications	Garden, park, playground, hotel, pools, etc
Fibra - Fibre - Faser - Fibre	PE Monofilament straight & PP Monofilament curled (UV Stabilized)
Tipo de Hilo - Yarn type - Garen type - type de fil	7.200 / 8 dTex monofilamento PP recto & 3.200 / 8 Dtex monofilamento PP rizado
Calidad de Hilo - Yarn quality - Qualité du fil - type de fil	Environmental friendly, free of lead and cadmium
Fabricación - Production - Produktion - Fabrication	Tufting
Calibre - Gauge - Teilung - Jauge	5/16
Altura de la fibra - Pile height - Polhöhe - Hauteur de la fibre	36 mm
Puntadas - Stitches - Stichzahl - Noeuds	17 ± 10 / 10 cm
Tufts - Tufts - Noppenzahl - Touffes	21.420 ± 10 / m ²
Longitud del rollo - Roll length - Rollenlänge - Longueur du rouleau	20-25m
Ancho del rollo - Roll width - Rollbreite - Largeur des rouleaux	4.0m or 2.0m
Peso de la fibra - Pile weight - Polgewicht - Poids de la fibre	1.892 gr/m ² ± 10%
Peso total - Total weight - Gesamtgewicht - Poids total	2.863 gr/m ² ± 10%
Composición de la fibra - Fibre composition - Zusammensetzung der Faser - Composition de fibre	Polyethylene + Polypropylene
Color - Colour - Farbe - Couleur	Monofilamento mezcla de verde claro y oscuro + hilo rizado color yute
Relleno - Infill - Verfüllung - Remplissage	Silica sand, gradation 0,5 - 1,0 mm, 80% roundshaped, appr. 6 - 8 kg/m ²
Refuerzo primario - Primary backing - Primary backing - Support primaire	100% PP black with fleece, UV Stabilized, Weight 135 gr/m ²
Refuerzo Secundario - Secondary backing - Secondary backing - Support secondaire	Black Latex compound with a base of styrenebutadiene (SBR), with drainage holes, Weight 836 gr/m ²
Estabilidad UV - UV stability - UV-Stabilität - Stabilité UV	Meets DIN 53387 Standard (6000 hours)
Revestimiento - Coating - Überzug - Revêtement	Black Latex compound with a base of styrenebutadiene (SBR), with drainage holes, Gewicht 836 gr/m ²
Permeabilidad al agua - Water Permeability - Wasserdurchlässigkeit - Perméabilité à l'eau	60 liters per minute per m ²
Fabricación - Fabrication - Fabrikazion - Production	Made in EU